

SLICK INSPECTION LTD.  
2038-12th AVE NW  
Medicine Hat, AB, T1C 2A7  
PH: 403-527-9854  
FAX: 403-527-9867  
office@slickinspection.com

## ULTRASONIC THICKNESS INSPECTION REPORT

Technician Sign:



Date:

Client:

DEC. 4, 2025

Technician Certification:

**JOHN MARTIN**  
CGSB Level II RT MT PT  
SNT-TC-1A Level II RT MT PT  
REG. #27301

Assistant:

Location:

Client Rep Signature:

RARE OILFIELD

RARE OILFIELD SHOP

Invoice #:

**JM25433**

Report #:

**JM25433-U1**

Page:

1 of 2

Acceptance Code:

Client Information

Specification:

Integrity Survey

Procedure:

UT-1 Rev.2

Technique:

UT - Thickness

Contractor:

A.F.E. #:

Code. #:

P.O. #:

Project:

Job. #:

### GLYCOL COIL TESTING

**COIL:**



**NAME PLATE:**



PERFORMED THICKNESS INSPECTION ON ABOVE COIL. INSPECTED RANDOM SPOTS AS REQUESTED FROM CLIENT.

#### Equipment, Calibrations & Consumables Used

Instrument Make:	AlphaGage+, Ser: 000128	Range Of Verification: 0.1" - 0.5"	Calibrated On: DEC. 4, 2025	Cable Length: 3 Feet	Cable Type: Coaxial	Test Method: Thickness > ✓ Lamination >	Couplant: Sonotech Soundsafe
Transduser Settings:	Sonatest Probe	Model: DK525	Calibrated On: DEC. 4, 2025	Angle: 0°	Frequency: 5 MHz	Size: 5 / .25"	Refrence & Scan /
Calibration Block:	Stainless 5 Step Wedge .100 - .500"	Block Serial #: S/N 3142 24	Calibrated On: DEC. 4, 2025	Reference Reflector: Backwall		Refernece %FSH 100%	Range Setting 1.0 Inches

## ULTRASONIC THICKNESS INSPECTION REPORT

SLICK INSPECTION LTD.  
2038-12th AVE NW  
Medicine Hat, AB, T1C 2A7  
PH: 403-527-9854  
FAX: 403-527-9867  
office@slickinspection.com

Technician Sign:

Technician Certification:

**JOHN MARTIN**  
CGSB Level II RT MT PT  
SNT-TC-1A Level II RT MT PT  
REG. #27301

Assistant:

Date:  
Client:

DEC. 4, 2025

Location:

RARE OILFIELD

Client Rep Signature:

RARE OILFIELD SHOP

Upon approval/acceptance by the Contractor the liability for the accuracy of final product becomes responsibility of the Contractor

Invoice #:

**JM25433**

Report #:

**JM25433-U1**

Page:

2 of 2

Acceptance Code:

Client Information

Specification:

Integrity Survey

Procedure:

UT-1 Rev.2

Technique:

UT - Thickness

Contractor:

A.F.E. #:

Code. #:

P.O. #:

Project:

Job. #:

Area Surface Readings: ↓		Nominal Wall Thickness:> ?		Average Thickness Reading:> 2.63mm		Area Surface Readings: ↓		Nominal Wall Thickness:> ?		Average Thickness Reading:> 2.71mm	
Location #:	Thickness Min:	Thickness Max:	Location #:	Thickness Min:	Thickness Max:	Location #:	Thickness Min:	Thickness Max:	Location #:	Thickness Min:	Thickness Max:
UT-1	2.35mm	2.51mm	UT-6	2.57mm	2.70mm	UT-11	2.48mm	2.60mm	UT-16	2.80mm	3.01mm
UT-2	2.55mm	2.64mm	UT-7	2.64mm	2.71mm	UT-12	2.53mm	2.66mm	UT-17	2.63mm	2.91mm
UT-3	2.65mm	2.80mm	UT-8	2.55mm	2.68mm	UT-13	2.70mm	2.90mm	UT-18	2.35mm	2.81mm
UT-4	2.60mm	2.71mm	UT-9	2.53mm	2.71mm	UT-14	2.68mm	2.81mm	UT-19	2.75mm	2.92mm
UT-5	2.65mm	2.81mm	UT-10	2.59mm	2.66mm	UT-15	2.73mm	2.90mm	UT-20	2.30mm	2.85mm



Information On Above: ↓ Material:> Carbon Steel Surface Condition:> Rusted

Information On Above: ↓ Material:> Carbon Steel Surface Condition:> Rusted

THICKNESS INSPECTION ON RANDOM POINTS.

THICKNESS INSPECTION ON RANDOM POINTS.